

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A01N 3/00, 59/14	A1	(11) International Publication Number: WO 97/14303 (43) International Publication Date: 24 April 1997 (24.04.97)
<p>(21) International Application Number: PCT/US96/16443</p> <p>(22) International Filing Date: 16 October 1996 (16.10.96)</p> <p>(30) Priority Data: 08/544,903 18 October 1995 (18.10.95) US</p> <p>(71) Applicant: U.S. BORAX INC. [US/US]; 26877 Tourney Road, Valencia, CA 91355-1847 (US).</p> <p>(72) Inventors: SCHUBERT, David, M.; 11252 Nebraska Avenue, Los Angeles, CA 90025 (US). MANNING, Mark, J.; 25919 Tournament Road #153, Valencia, CA 91355 (US).</p> <p>(74) Agent: THORNTON, James, R.; 26877 Tourney Road, Valencia, CA 91355-1847 (US).</p>		<p>(81) Designated States: AL, AM, AU, BB, BG, BR, CA, CN, CZ, EE, FI, GE, HU, IL, IS, JP, KG, KP, KR, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, TR, TT, UA, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: COMPOSITIONS AND METHODS FOR PRESERVING WOOD PRODUCTS</p> <p>(57) Abstract</p> <p>Lumber, plywood and other wood products are preserved from attack by fungi, termites and wood-destroying insects as well as fire and flame by treatment with a novel zirconium borate-containing preservative composition. The preservative can be formed by combination of a source of boron such as boric acid and the water-soluble salts thereof with a water-soluble zirconium salt. The ZrO₂:B₂O₃ weight ratio in the preservative composition is in the range of from about 0.75:1 to about 10:1.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

COMPOSITIONS AND METHODS FOR PRESERVING WOOD PRODUCTS

This invention relates to the preservation of wood and more particularly, this invention provides novel compositions and methods for preserving wood products, such as lumber, plywood, poles, railroad crossties and the like, by use of borate based preservative and fire-retardant compositions combined with soluble zirconium salts.

BACKGROUND OF THE INVENTION

Inorganic boron compounds have been used as wood preservatives and fire retardants for many years. The basic materials, boric acid and borax, are readily available, inexpensive and relatively harmless to humans, and their toxicity to fungi, termites, and wood-destroying insects has been clearly established. At higher levels of treatment, the borates are also effective as fire-retardants for lumber and other wood products. However, since the commonly used borates are readily soluble in water, their use has been restricted to applications where leaching is not likely to occur, such as by rain water or soil moisture. In order to alleviate this limitation, various means for insolubilizing or fixing the borate in the wood have been proposed. For example, Du Fresne et al., U. S. Patent 3,306,765, shows impregnation of wood with a mixture of sodium silicate and borax and then treatment with carbon dioxide under pressure to fix the fireproofing agents against leaching. See also USSR Patent 283,546 (Chemical Abstracts 75, 75338) and Japanese Kokai Tokkyo Koho 62,275,703 (Chemical Abstracts 108, 169476) which propose treating with a soluble borate-containing preservative and then altering the pH such as with ammonia to precipitate insoluble preservatives in the wood.

Water-soluble zirconium salts are known and have various uses such as for insolubilizing starch binders used in paper coating compositions and to impart thixotropy to dispersions of polymers such as emulsion paints. See Phillips U. S. patent 4,097,430.

Water-insoluble salts of metals such as copper, mercury and nickel are known to be fungicidal and can be solubilized by mixing with zirconyl acetate in acetic acid solution or with zirconyl ammonium carbonate solutions to provide compositions for rendering

cotton fabric rot-resistant. See Conner, U. S. Patents 3,183,118 and 3,291,635.

Copper borate and phenyl mercury borate are among the metal salts that may be used. For example, cotton fabric can be treated with solubilized copper borate and then cured, such as by heating at 145 C., to convert the soluble form to an insoluble form.

5 Subsequently, Conner et al. substituted copper carbonate for copper borate. See Textile Chemist and Colorist, April 1978, and see Sherif et al. U. S. Patent 4,274,972, which claims a process for preparing an improved dilute aqueous copper zirconium ammonium carbonate solution, having enhanced resistance to gelation.

Japanese Kokai Tokkyo Koho 58,164,673 (1983) (Chemical Abstracts, Vol. 100, 54052) describes preparation of a fireproofing agent from a mixture of acidified shellfish fossils and siliceous soil with a solution of boric acid, borax and zirconium silicate.

Although a simple zirconium borate has not been well-defined, anhydrous and hydrated zirconium borates are reviewed in Supplement to Mellor's Comprehensive
15 Treatise on Inorganic and Theoretical Chemistry, Volume V, Part A, Pages 618-619 (1980).

SUMMARY OF THE INVENTION

20 The present invention provides novel aqueous borate preservative compositions for wood products comprising an aqueous solution of 1) a source of boron selected from the group consisting of boric acid and the water-soluble salts thereof and 2) a water-soluble zirconium salt, wherein the $ZrO_2:B_2O_3$ weight ratio in said preservative composition is about 0.75:1 to 10:1. There are also provided methods for preserving
25 wood products which comprise treating the wood products with the aqueous borate preservative according to this invention. Preservation includes protection against fire as well as controlling fungi, termites and wood-destroying insects.

DETAILED DESCRIPTION OF THE INVENTION

The preservative compositions of this invention are prepared by admixing one or more of the boron compounds with the zirconium salt in an aqueous solution.

5 Alternatively, the compositions may be formed within the lumber products to be protected. For example, the lumber product can be treated first with a solution of the zirconium salt and then treated with an aqueous solution of the boron compound, thereby forming the preservative composition within the structure of the wood. However, it is preferred that the preservative composition is formed prior to treatment
10 of the wood.

In the preparation of the preservative compositions, the source of boron is combined with the water-soluble zirconium salt, such as in an aqueous solution. For example, one or more of the boron compounds may be dissolved in an aqueous solution of the zirconium salt or a solution of boron compound may be combined with a solution
15 of the zirconium salt. The amount of boron compound and zirconium salt is adjusted so that the resultant preservative composition has a $ZrO_2 \cdot B_2O_3$ weight ratio of from about 0.75:1 to about 10:1, preferably from about 1.5:1 to about 3.5:1. The resultant preservative compositions may be diluted, if desired, prior to use as a wood treatment, or they may be used in concentrated form.

20 The source of boron can be one or more of boric acid and/or the water-soluble salts of boric acid, such as sodium tetraborate decahydrate (borax), sodium tetraborate pentahydrate, sodium octaborate tetrahydrate, sodium metaborate, sodium perborate hydrates, potassium tetraborate, sodium pentaborate, ammonium pentaborate hydrate, anhydrous sodium tetraborate, potassium metaborate, and the like. Preferably, the
25 boron compound is sodium octaborate tetrahydrate or a mixture of boric acid and sodium tetraborate pentahydrate. Sodium octaborate tetrahydrate is commercially available as *Tim-bor*[®] wood preservative from U. S. Borax Inc., Valencia, California.

The zirconium salt may be any of the water-soluble zirconium salts, especially the commercially available solutions of zirconium salts such as ammonium zirconium
30 carbonate, zirconium acetate, zirconium propionate, zirconium orthosulfate, potassium zirconium carbonate, zirconium hydroxychloride, zirconium oxychloride, zirconium

nitrate, and acidic solutions of zirconium basic carbonate. A particularly useful zirconium salt is commercially available as an aqueous solution of ammonium zirconium carbonate (containing 20% by weight ZrO_2) under the name Bacote 20 from Magnesium Elektron Ltd.

5 In practicing the method of this invention, the wood product is treated with the preservative solution in a manner and with an amount sufficient to impregnate the wood with the preservative solution and deposit an effective amount of preservative in the structure of the wood. The treatment may be by spraying or by merely dipping the wood article in the preservative solution and allowing it to soak for a time sufficient to
10 diffuse the preservative throughout the wood, or the treatment may be under pressure and/or vacuum. The effective amount of preservative in the wood will be dependent upon the nature of the protection desired. For example, if preservation from attack by fungi, termites and wood-destroying insects is desired, the amount of preservative in the wood should be in the range of from about 0.5 to about 2.5% by weight boric acid
15 equivalent (about 0.3 to about 1.5% B_2O_3). If preservation from fire is the goal (fire-retardant), an effective amount is in the range of from about 10 to about 15% by weight, boric acid equivalent (about 5 to about 9% B_2O_3). After treatment, the wood product is allowed to dry in the air to a constant weight or it may dried by heating, such as in an kiln, thereby providing a leach-resistant zirconium borate complex in the wood.
20 Preferably, the treated article is heated, such as at a temperature of from about 50° to about 105°C, to accelerate drying and to provide the best leach-resistant properties to the wood.

In an alternative treatment procedure, the wood product may be treated in two steps such as by first treating with the zirconium salt solution and then treating with an
25 aqueous solution of the boron compound. Alternatively, the order of treatments may be reversed. However, the preferred procedure is to treat the wood product with the preformed preservative solution containing the boron - zirconium composition of this invention.

The resultant treated wood products are preserved against the ravages of fungi,
30 termites, and wood destroying insects, and if a sufficient amount of preservative is employed, is resistant to fire. The preservative is "fixed" in the wood product and is

therefore resistant to leaching by moisture, making it especially useful for outdoor or ground contact service such as decking, utility poles, exterior siding, outdoor furniture, etc.

The following examples illustrate the novel preservative compositions and the
5 methods of this invention:

EXAMPLE I

Sodium octaborate tetrahydrate (20 g.) was dissolved in 500 g. of an aqueous
10 solution of ammonium zirconium carbonate containing 20% by weight ZrO_2 (Bacote 20) and 480 g. of deionized water. Bacote 20 is a commercially available aqueous solution which nominally contains 20% ZrO_2 , 8% NH_3 , and 13% CO_2 , all by weight. The resulting solution contained 2% of sodium octaborate (1.34% B_2O_3) and 10% zirconium oxide.

15

EXAMPLE II

Ammonium pentaborate (10 g.) and 50 g. of Bacote 20 ammonium zirconium carbonate solution were combined in 40 g. of deionized water to give 100 g. of a clear
20 solution containing 10% of ZrO_2 and 6.4% of B_2O_3 .

EXAMPLE III

Ammonium pentaborate (39.09 g.) and 125.0 g. of Bacote 20 ammonium
25 zirconium carbonate solution were combined with 85.91 g. of deionized water to give 250 g. of a clear solution containing 10% ZrO_2 and 10% B_2O_3 .

EXAMPLES IV - X

30 A series of seven wood preserving solutions were prepared from boric acid and ammonium zirconium carbonate by dissolving 8.88 grams of boric acid in varying

amounts of Bacote 20 ammonium zirconium carbonate solution which had been diluted with deionized water. Effervescence was noted in each case when the boric acid was added to the solutions, indicating the evolution of carbon dioxide gas. The resultant solutions contained 5% B_2O_3 and from 2.5 to 17.5% ZrO_2 and had a ZrO_2/B_2O_3 ratio ranging from 0.5 to 3.5. The pH of the solutions ranged from 7.25 to 8.73. Each solution was placed in an evaporating dish and allowed to evaporate down to dryness at room temperature. After two weeks the remaining residue of each solution was a clear, glassy solid, which formed either a monolith or cracked into a few solid fragments. Samples of the clear solid residues were heated at 105°C overnight to give opaque glasses. The opaque glasses were ground to fine powders using a shatter box and a 5.00 g. sample of each powder was placed in a 100 ml. soda lime (non-borosilicate) glass jar. Based on the compositions of the starting solutions, these 500 g. samples were calculated to have the following compositions.

15

Table 1

<u>Example</u>	<u>% B_2O_3</u>	<u>g B_2O_3</u>	<u>ZrO_2/B_2O_3 Weight Ratio</u>
IV	38.6	1.93	0.5
V	29.7	1.48	1.0
VI	23.8	1.19	1.5
VII	19.8	0.99	2.0
VIII	17.0	0.85	2.5
IX	15.1	0.76	3.0
X	13.6	0.68	3.5

Deionized water (45.00 g.) was added to each jar to make 10% by weight glass powder slurries. The jars were sealed and allowed to stand at room temperature for 26 days. Each day, the slurries were shaken to resuspend the solids in each jar. At the end of the 26 day test period, the solids were separated by filtration and the clear supernatant solutions were analyzed for borate content to determine the amount of

borate that had leached out of the glasses. The following results were obtained as shown in Table 2.

<u>Example</u>	Table 2			
	<u>g B₂O₃</u> <u>in Sample</u>	<u>% B₂O₃</u> <u>in Leachate</u>	<u>g B₂O₃</u> <u>Leached</u>	<u>% B₂O₃</u> <u>Leached</u>
IV	1.93	3.57	1.78	92.0
V	1.48	2.04	1.02	68.9
VI	1.19	1.36	0.68	57.1
VII	0.99	1.06	0.50	50.5
VIII	0.85	0.85	0.42	49.4
IX	0.76	0.81	0.40	52.6
X	0.68	0.71	0.36	52.9

5

Although a portion of the borate was leached from the samples under the rigorous test conditions, a substantial amount of borate remained, especially at the preferred ZrO₂:B₂O₃ ratios of from about 1.5:1 to about 3.5:1. Accordingly, a substantial amount of borate would remain in the dried preservative composition under very rigorous leaching conditions such as by constant rain or water immersion over a long period of time.

10

EXAMPLE XI - XIII

15

Sodium octaborate tetrahydrate (40 g.) was dissolved in each of three samples containing 200, 500 and 1000 grams of Bacote 20 ammonium zirconium carbonate solution which had been diluted with sufficient deionized water to give 2000 g. of a final solution containing 2.0% by weight sodium octaborate (1.34% B₂O₃) and 2%, 5% and 10%, respectively, by weight of ZrO₂. The pH of the resultant clear solutions was 8.82, 9.05 and 9.23, respectively. The solutions were used to pressure treat Southern Yellow Pine cubes according to the following procedure, in which Example XI contained 2%

20

ZrO₂. Example XII contained 5% ZrO₂ and Example XIII contained 10% ZrO₂. Each example also contained 1.34% B₂O₃.

Cubes (3/4 inch) of Southern Yellow Pine were pressure treated with the ammonium zirconium borate solutions by placing the cubes in a tray and weighting them down with plastic coated lead weights. The treating solutions were then poured into the container, completely covering all the cube samples. The treating cycle consisted of a short vacuum cycle (5 minutes at 28 " Hg) followed by a 30 minute pressure cycle at 140 psi. The samples were weighed initially and then again following pressure treatment; chemical retentions were then calculated using the weight difference and solution concentration. The treated samples were dried by heating in a 50°C. oven for about 24 hours.

Leach tests were performed according to the procedure of the American Wood Preservers' Association Standard E11-87: Standard Method of Determining the Leachability of Wood Preservatives. The treated samples were vacuum impregnated with distilled water (28 " Hg for 20 minutes) and a sample of the resulting solution taken and analyzed for boron to obtain leach results after the 20 minute treatment. The initial solution was discarded and the saturated wood samples were submerged in fresh distilled water. Periodically, up to a total of 240 hours, a sample of leachant were removed and then the samples were again submerged in fresh distilled water. The collected samples were all analyzed for boron using Inductively Coupled Plasma-Atomic Emission Spectroscopy (ICP-AES). The results are shown in the following Table A.

Table A

Percent of Initial Boron Content
Contained in Cubes After Leaching

<u>Sample</u> <u>Number</u>	<u>Leach Time</u> <u>(Hours)</u>	<u>Example XI</u>	<u>Example XII</u>	<u>Example XIII</u>
1	0.33	87	94	97
2	2	74	89	95
3	4	65	84	92
4	24	35	60	77
5	29	28	54	74
6	53	18	40	66
7	77	12	31	59
8	146	7	18	47
9	191	6	13	42
10	240	5	9	37

The tests were repeated using small coupons of the wood with nominal dimensions of 5/8" thick x 4" long x 1.5" wide. The procedure was the same except
5 samples of leachant were taken and analyzed up to a total of 1582 hours (66 days) and each treatment was replicated. The following results were obtained as shown in Table B in which the replicates are identified as A and B.

Table B
Percent of Initial Boron Content Retained in Cubes After Leaching

<u>Sample Number</u>	<u>Leach Time (Hours)</u>	<u>Example XI</u>		<u>Example XII</u>		<u>Example XIII</u>	
		<u>(A)</u>	<u>(B)</u>	<u>(A)</u>	<u>(B)</u>	<u>(A)</u>	<u>(B)</u>
1	0.33	92	92	98	98	99	99
2	2	85	85	95	95	97	97
3	4	81	81	93	93	96	96
4	23	65	65	80	81	90	90
5	28	62	62	78	78	89	88
6	46	55	55	70	71	84	84
7	76	46	46	59	60	77	76
8	100	41	41	52	53	71	70
9	169	31	32	41	40	60	58
10	214	27	28	36	35	54	52
11	263	25	26	31	31	49	48
12	336	22	23	27	26	44	42
13	700	19	20	22	20	36	37
14	1032	17	18	19	17	31	33
15	1582	16	17	16	14	26	28

EXAMPLE XIV

5

Boric acid (23.98 grams; 0.39 mole) was dissolved in 476.02 grams of deionized water and this solution was then added to 500 grams of Bacote 20 ammonium zirconium carbonate solution. The resultant 1000 grams of clear solution contained 1.35% by weight B_2O_3 and 10% by weight ZrO_2 .

10

EXAMPLE XV

Boric acid (24.78 grams; 0.40 mole) was dissolved in 490.0 grams of deionized water and this solution was then added to 512 grams of zirconium acetate solution
5 containing 22% ZrO_2 . The resultant 1026.8 grams of clear solution contained 1.35% by weight B_2O_3 and 11% by weight ZrO_2 .

EXAMPLE XVI

10 Sodium octaborate tetrahydrate (20 g.) was dissolved in 500 g. of a clear, alkaline aqueous solution of potassium zirconium carbonate containing about 20% by weight ZrO_2 (commercially available as Zirmel 1000) and 480 g. of deionized water. The resulting clear solution contained 2% of sodium octaborate (1.34% B_2O_3) and 10% zirconium oxide.

15

Various changes and modifications of the invention can be made and, to the extent that such variations incorporate the spirit of this invention, they are intended to be included within the scope of the appended claims.

CLAIMS

WHAT IS CLAIMED IS:

1. An aqueous borate preservative composition for wood products comprising an aqueous solution of 1) a source of boron selected from the group consisting of boric acid and the water-soluble salts thereof and 2) a water-soluble zirconium salt, in which the $\text{ZrO}_2\cdot\text{B}_2\text{O}_3$ weight ratio is about 0.75:1 - 10:1 and which, upon drying, said preservative composition forms a zirconium borate complex which is resistant to leaching by moisture.
2. An aqueous borate preservative composition according to claim 1 in which said water-soluble zirconium salt is selected from the group consisting of ammonium zirconium carbonate, zirconium acetate, zirconium propionate, zirconium orthosulfate, potassium zirconium carbonate and acidic solutions of zirconium basic carbonate.
3. An aqueous borate preservative composition according to claim 1 in which said source of boron is a sodium borate.
4. An aqueous borate preservative composition for wood products comprising an aqueous solution of sodium octaborate tetrahydrate and ammonium zirconium carbonate, in which the $\text{ZrO}_2\cdot\text{B}_2\text{O}_3$ weight ratio is about 0.75:1 - 10:1.
5. An aqueous borate preservative composition according to claim 1 in which said source of boron is boric acid.
6. An aqueous borate preservative composition according to claim 1 in which said $\text{ZrO}_2\cdot\text{B}_2\text{O}_3$ weight ratio is about 1.5:1 to 3.5:1.

7. The method for preserving wood products against fungi, insects and fire, which comprises treating said wood product with a fungicidal, insecticidal and fire-retardant amount of 1) a borate selected from the group consisting of boric acid and the water-soluble salts thereof and 2) a water-soluble zirconium salt, and drying said treated wood product, thereby depositing in said wood product a zirconium borate complex which is resistant to leaching by moisture, wherein the $\text{ZrO}_2\text{:B}_2\text{O}_3$ weight ratio is about 0.75:1 to 10:1 and wherein the resultant preserved wood product contains about 0.3 to about 9% by weight B_2O_3 .

8. The method according to claim 7 in which said $\text{ZrO}_2\text{:B}_2\text{O}_3$ weight ratio is about 1.5:1 to 3.5:1.

9. The method according to claim 7 in which a zirconium borate complex, which is resistant to leaching by water, is formed in said wood product.

10. The method according to claim 7 in which said wood product is dried by heating at a temperature in the range of from about 50°C to about 105°C.

11. The method according to claim 7 in which said wood product is treated by soaking in an aqueous preservative solution comprising said source of boron and said water-soluble zirconium salt for a period of time sufficient to diffuse said preservative solution throughout said wood product.

12. The method according to claim 7 in which said wood product is treated with an aqueous preservative solution comprising said source of boron and said water-soluble zirconium salt under pressure so as to distribute said preservative solution throughout said wood product.

13. The method according to claim 7 in which a fire-retardant amount of said zirconium borate complex is deposited in said wood product.

14. The method according to claim 7 in which an insecticidal amount of said zirconium borate complex is deposited in said wood product.
15. Wood products containing an insecticidal and fire-retardant amount of a zirconium borate preservative which is resistant to leaching by water.
16. Wood products according to claim 15 containing from about 0.3 to about 9 % by weight B_2O_3 .
17. A fire-retardant wood product containing a fire-retardant amount of a zirconium borate complex which is resistant to leaching by water, said wood product containing about 5 to about 9 % by weight B_2O_3 .
18. A wood product which is resistant to attack by fungi and insects, containing an insecticidal amount of a zirconium borate complex in which the $ZrO_2:B_2O_3$ weight ratio is about 0.75:1 to 10:1.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US96/16443

A. CLASSIFICATION OF SUBJECT MATTER IPC(6) : A01N 3/00, 59/14 US CL : 106/15.05, 18.13, 18.3; 424/617, 657, 658, 659, 660; 427/297, 397, 427, 440; 428/537.1 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 106/15.05, 18.13, 18.3; 424/617, 657, 658, 659, 660; 427/297, 397, 427, 440; 428/537.1 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,207,823 A (SHIOZAWA) 04 MAY 1993, see abstract.	1-18
A	UK 2,114,003 A (BIO-KIL LABORATORIES) 17 AUGUST 1983, see abstract and claims.	1-18
A	Z-PLEX 9000, MAGNESIUM ELEKTRON DATA SHEET 9000 (provisional), undated, see page 1.	1-18
A	BACOTE 20, MAGNESIUM ELEKTRON DATA SHEET 722, February 1991, see page 1.	1-18
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understate the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art *Z* document member of the same patent family	
Date of the actual completion of the international search 08 NOVEMBER 1996		Date of mailing of the international search report 21 FEB 1997
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer fw ANTHONY J. GREEN Telephone No. (703) -308-3819